

Component - Plastics

E194507

LG MMA CORP

TECH-TEAM 759 CHUNGHENG-DONG, YEOSU-SHI CHUNRANAM-DO 555-805 KR

IF-870(#)

Polymethyl Methacrylate (PMMA), furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	HB	-	-	50	50	50

Comparative Tracking Index (CTI): -

High-Voltage Arc Tracking Rate (HVTR): -

Dielectric Strength (kV/mm): -

Dimensional Stability (%): -

High Volt, Low Current Arc Resis (D495): -

Volume Resistivity (10^x ohm-cm) : -

(#) - May be replaced by one letter from A to Z.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1999-03-18

Last Revised: 2008-06-04

Underwriters Laboratories Inc®



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
Glow-Wire Flammability (GWI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWI)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m²	-	-
ISO Izod Impact	ISO 180	kJ/m²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m²	-	-
Underwriters Laboratories Inc®				